


<b>Manufacturer Distributor</b>		Rolf Bayer Vacuumverpackung GmbH Reitweg 9 D-90587 Veitsbronn Deutschland / Germany		Tel. +49 (0) 911-7808-0 Fax: +49 (0) 911-7808-111 / -115 E-Mail: info@rbayer.de Homepage: www.rbayer.de	
Article	Article		Width x Length		Motive
	Material		Valid for all sizes!		
	Material				
	Material				
	Material				
	<b>Description</b>		Three seal bags		
<b>Type</b>		RBS-150			
Printing	Printing method		<input checked="" type="checkbox"/> unprinted		<input checked="" type="checkbox"/> transparent
			<input type="checkbox"/> flexo printing		<input type="checkbox"/>
			<input type="checkbox"/> copper gravure printing		<input type="checkbox"/>
Detailed information from inside to outside			from light to dark		Tolerant
Measurements	Thickness	µm	23 °C/ 50%RH	140	DIN 53370 / ASTM E 252
	Grammage	g/m <sup>2</sup>		135,7	DIN 53365 / ASTM D 1505
	Yield	m <sup>2</sup> /kg		7,4	
	Metre per roll	Pieces per carton			
	Metre per pallet	Pieces per pallet			
Properties	Number of layers		multilayer		
	Structure of layers		compound of PA/PE		
	Laminating adhesive				
	Antifog		<input checked="" type="checkbox"/> No <input type="checkbox"/> Yes		
	Peel		<input checked="" type="checkbox"/> No <input type="checkbox"/> Yes		
Permeability	Oxygen O <sub>2</sub>	cm <sup>3</sup> /m <sup>2</sup> *d*bar	23 °C/ 0% r.h.	< 40	DIN 53380
	Nitrogen N <sub>2</sub>				DIN 53380
	Carbon dioxide CO <sub>2</sub>				DIN 53122
	Water Vapour H <sub>2</sub> O	g/m <sup>2</sup> *d	23 °C/ 85% r.h.	< 3	DIN 53122
Mechanic Properties	Tensile at break	along	N/15mm	23 °C/ 50% r.h.	60
		across			55
	Elongation at break	along	%	200 - 300	DIN 53455-6
		across		250 - 400	
	Gloss / Haze		% / Units		
Seal strenght		N/15mm	150 °C, 1sec., 5 atm	> 25	
Appli- cation	Sealing range		°C	120 - 160	machine- and product-dependent
	Plasticity		°C		
	<input checked="" type="checkbox"/> Suitable for freezing up to -25 °C.		<input checked="" type="checkbox"/> Food law compliance - in detail see "declaration of conformity".		
Veitsbronn, actual state: 2 <sup>rd</sup> Nov. 2017			<b>This specification is valid until recalled!</b>		
Rolf Bayer Vacuumverpackung GmbH Christian Frericks (DGQ Quality Manager)			 <b>ROLF BAYER</b> VACUUMVERPACKUNG GmbH REITWEG 9 D-90587 VEITSBRONN TEL.: (09 11) 78 08-0 FAX: (09 11) 78 08-111		

Storage conditions: Storage temperature from 18 °C to 25 °C in enclosed spaces, Air humidity: 40% to 56% r.h.

The information contained herein is to the best of our knowledge accurate, but since the circumstances in which it may be used are beyond our control we do not accept liability for any loss or damage that may occur nor do we offer any warranty of immunity against patent infringement. The values indicated in the table only describe typical properties, but do not constitute specification limits.

BRC/loP Global Standard	Anzahl Seiten:	1 von 1	Erstellung:	Christian Frericks (-257)
Version: 01	Fassung vom:	01.12.2008	Prüfung und Freigabe:	Christian Frericks (-257)

N:\QS\Kunden-Nachweise+Spez. = Info an CF bei Änderungen\10495 ROLF BAYER Spezifikationen Vorlagen\Spec. RBS-150 Three Seal Bags.doc